

CLAIMS

1. A substituted polyaniline polymer capable of converting between a self-doped form and a non-self doped form by a reversible chemical reaction.


5 2. The polymer according to claim 1 having a hardness of at least 0.03 GPa.

3. The polymer according to claim 1 having a molecular weight of at least 10,000.

4. The polymer according to claim 1 having a molecular weight of  
10 at least 100,000.


5. A polymer capable of converting between a self-doped form and a non-self doped form by a reversible chemical reaction.

6. A self-doped polyaniline capable of converting between:  
a water-soluble self-doped form comprising repeating units as shown  
15 below



20 ; and

a water-insoluble non-self-doped form comprising repeating units as shown below:



25

wherein the water-soluble form is converted to the water-insoluble  
 5 form by reducing fluoride concentration of the polymer.

7. The polyaniline according to claim 6 having a hardness of at least 0.03 GPa.


8. The polyaniline according to claim 6 having a molecular weight of at least 10,000.

10 9. The polyaniline according to claim 6 having a molecular weight of at least 100,000.

10. A method of making a self-doped polyaniline comprising:

(a) providing a monomer:


15




, D-fructose and fluoride;

(b) incubating said monomer, the D-fructose and the fluoride under  
 20 conditions suitable for polymerization, thereby producing a first polymer:

25



(c) precipitating said polymer by reducing the fluoride concentration, thereby producing a second polymer:



5

11. The method according to claim 10 including:

(d) heating the second polymer, thereby forming a cross-linked polymer.

10

12. The method according to claim 10 having a hardness of at least 0.03 GPa.

13. The method according to claim 10 having a molecular weight of at least 10,000.

14. The method according to claim 10 having a molecular weight of at least 100,000.

15